




# LINE MAKER

## LIGHTFAST PIGMENT INK

	LF
 Black 0.05 / 0.1 / 0.2 / 0.3 / 0.5 / 0.8	8
 Sepia 0.1 / 0.3 / 0.5	4
 Graphite 0.1 / 0.3 / 0.5	8

- Pack of 6 Black (0.05 / 0.1 / 0.2 / 0.3 / 0.5 / 0.8) • Pack of 3 Black (0.1 / 0.3 / 0.5)
- Pack of 3 Sepia (0.1 / 0.3 / 0.5) • Pack of 3 Graphite (0.1 / 0.3 / 0.5)

LF - Lightfastness rating

Lightfastness refers to the chemical stability of a pigment under long exposure to light. Light can cause colour to whiten, darken, fade or completely disappear.

The Blue Wool Scale - two pieces of blue wool are used to test lightfastness. One is placed in the dark and the other in the equivalent of sunlight for a period of three months. After three months the two pieces of wool are compared and rated between 0 – 8. 8 is the highest rating and values of 6 or higher are considered to be lightfast.